

Miskolc IPW
IV. Sustainable Raw Materials
International Project Week

PROCEEDINGS





EFOP-3.6.2-16-2017-00010 "Sustainable Raw Material Management Thematic Network – RING 2017" Project



MISKOLCI
EGYETEM
UNIVERSITY OF MISKOLC

**PROCEEDINGS OF THE MISKOLC IPW -
IV. SUSTAINABLE RAW MATERIALS INTERNATIONAL PROJECT WEEK
25-27TH NOVEMBER 2020, MISKOLC, HUNGARY**

**A MISKOLC IPW - IV. FENNTARTHATÓ
NYERSANYAG-GAZDÁLKODÁS PROJEKTHÉT KIADVÁNYA
2020. NOVEMBER 25-27. MISKOLC, MAGYARORSZÁG**

Scientific Committee:

DR. HABIL JÓZSEF FAITLI, *University of Miskolc*
PROF. DR. GÁBOR MUCSI, *University of Miskolc*
DR. SÁNDOR NAGY, *University of Miskolc*
DR. HABIL GÁBOR RÁKHELY, *University of Szeged*
PROF. DR. CECÍLIA HODÚR, *University of Szeged*
DR. HABIL IMRE CZUPY, *University of Sopron*
DR. ZOLTÁN PÁSZTORY, *University of Sopron*
CSABA VÉR, *University of Pécs*
DR. TIBOR KISS, *University of Pécs*

Edited by:

DR. HABIL JÓZSEF FAITLI, *University of Miskolc*

ISBN of the web published version: <https://www.miskolcipw.hu/proceedings/>

ISBN 978-963-358-222-0

ISBN of the pendrive publication:

ISBN 978-963-358-223-7

Publisher: Institute of Raw Material Preparation and Process
Engineering, University of Miskolc
Address: Hungary, 3515 Miskolc-Egyetemváros
Telephone: +36 46 565 111/ 17-13; *and fax:* +36 46 565 054
E-mail: ejtadmin@uni-miskolc.hu
Web: <https://ejt.uni-miskolc.hu/>

SZÉCHENYI 2020



Európai Unió
Európai Szociális
Alap



BEFEKTETÉS A JÖVŐBE



PLENARY LECTURES ABSTRACTS

- P1 **Baláz M:** MECHANOCHEMISTRY: SUSTAINABLE TOOL FOR THE TREATMENT OF RAW MATERIALS AND WASTE
- P2 **Nenadović M:** STRUCTURAL, PHYSICOCHEMICAL AND RADIOLOGICAL CHARACTERIZATION OF GEOPOLYMERS

SESSION PAPERS

Session 1

- A12 **Bokányi Lj, Krizsán Gy, Takács J, Faitli J, Má dai-Üveges V, Ayu Janetasari S, Pintér-Móricz Á:** EVALUATION OF EFFICIENCY OF HYDRODYNAMIC TREATMENT ON SEWAGE SLUDGE pp. 1-8.
- A14 **Janetasari S A, Olviani A, Hamidah U, Widyarani, Sintawardani N, Bokányi L:** THE POTENTIAL OF ACETONITRILE DEGRADATION USING ANAEROBIC MICROBIC CONSORTIUM pp. 1-15.

Session 2

- B21 **Vágvölgyi A, Mészáros I, Czupy I:** ISZAPKOMPOSZT ANYAGMÉRLEGÉNEK VIZSGÁLATA pp. 1-9.
- B22 **Somfai D, Czakó-Vér K, Suhajda E, Dolgosné Kovács A, Dittrich E:** TESTING WASTE MATERIALS AS STAND-ALONE BIOGAS SUBSTRATES: METHANE YIELD OF DAIRY BY-PRODUCTS AND KITCHEN WASTE IN LABORATORY CONDITIONS pp. 1-7.
- B23 **Fülöp Zs, Czupy I:** MIKROBIOLÓGIAI TALAJOLTÓ KÉSZÍTMÉNYEK HATÁSA ÉS KIJUTTATÁSI MÓDSZERE pp. 1-8.
- B24 **Vizvári Z, Gyórfi N, Klincsik M, Sári Z, Odry P:** ÚJ MEGKÖZELÍTÉSŰ ELEKTROMOS IMPEDANCIA TOMOGRÁFIÁS REKORNSTRUKCIÓS ALGORITMUS ÁLTALÁNOSÍTÁSA TETSZŐLEGES MÉRETŰ HÁLÓZATRA pp. 1-20.
- B25 **Papp V, Szalay D:** MEZŐGAZDASÁGI MELLÉKTERMÉKEKBŐL KÉSZÜLT KEVERÉK PELLETEK ENERGETIKAI VIZSGÁLATAI pp. 1-5.

Session 3

- A31 **Alshkih A, Czupy I:** ASSESSMENT OF BIOMASS QUALITY OF SOME TREE'S SPECIES FOR BIOENERGY PRODUCTION pp. 1-8.
- A33 **Agarwal C, Pásztory Z:** TIP-ENHANCED RAMAN SPECTROSCOPY FOR NANOSCALE CHARACTERIZATION OF MATERIALS pp. 1-5.
- A34 **Yanar N:** LAB-SCALE INVESTIGATION OF RAMAN SPECTROSCOPY FOR PLASTICS RECYCLING pp. 1-9.
- A35 **Sukmana H, Hodúr C:** GRAIN/RICE HUSK AND GRAIN/RICE HUSK ASH UTILIZATION IN THE WASTEWATER TREATMENT pp. 1-6.



Session 4

- B41 **Szigony J, Kondor T, Vér Cs:** INNOVATÍV MEGOLDÁSOK, TERMÉSZETES ANYAGOK A FENNTARTHATÓ ÉPÍTÉSZETBEN -SOLAR DECATHLON 2019 pp. 1-9.
- B42 **Gyórfi A, Jakab A R, Leitold Cs, Kiss T:** MENNYISÉGI VÁLTOZÁSOK EGY LAKOSSÁGI VEGYES SZELEKTÍV HULLADÉKOT KEZELŐ KÉZI VÁLOGATÓMŰBEN pp. 1-7.
- B43 **Gyórfi A, Rostás A K, Leitold Cs, Kiss T:** HULLADÉKBÓL SZÁRMAZTATOTT TÜZELŐANYAG NEHÉZFÉM-TARTALMÁNAK VIZSGÁLATA pp. 1-7.
- B44 **Romenda R, Szalai P, Fajtli J:** SZABÁLYOS ALAKÚ SZEMCSÉK KÖZEG-ELLENÁLLÁSÁNAK VIZSGÁLATA EGYEDI FEJLESZTÉSŰ LÉGCSATORNÁBAN pp. 1-8.
- B45 **Gazdag G, Kondor T, Kokas B, Dolgosné Kovács A:** SZERKEZET OPTIMALIZÁCIÓ pp. 1-7.

Session 5

- A51 **Anh L D H, Pásztor Z:** REVIEW OF THE EFFECT OF MOISTURE CONTENT IN THERMAL CONDUCTIVITY OF NATURAL FIBER INSULATING MATERIALS pp. 1-5.
- A52 **Karacaoglan G, Halyag N, Mucsi G:** COMPARATIVE INVESTIGATION OF ZEOLITE GRINDING IN STIRRED MEDIA MILL AND PLANETARY BALL MILL pp. 1-10.
- A53 **Pásztor Z, Keresztfalvi P:** MOBILEFORESTER AS A NEW INNOVATIVE MEASURING DEVICE IN FORESTRY pp. 1-5.
- A54 **Romenda R, Tóth A, Virág Z:** PRIMARY AND SECONDARY MINING POSSIBILITIES OF CRITICAL ELEMENTS OF ELECTRONIC WASTE pp. 1-10.
- A55 **Wikurendra E A, Nagy I:** UTILIZATION OF BLACK SOLDIER FLY (HERMETIA ILLUCENS) AS A PROBLEM SOLVE OF ORGANIC SOLID WASTE pp. 1-10.

Session 6

- B61 **Juhász H, Kondor T, Dolgosné Kovács A:** ÚJRAHASZNOSÍTOTT NEMZETI IDENTITÁS pp. 1-6.
- B62 **Szűcs E, Kondor T, Vér Cs:** PASSZÍV ENERGIATEREK (SDE 19) pp. 1-5.
- B63 **Molnár J, Debreczeni Á:** ÁSVÁNYI ÉS MÁS ÉPÍTÉSI EREDETŰ HULLADÉK ANYAGOKBÓL KÉSZÍTETT HŐSZIGETELŐ KOMPOZITOK MŰSZAKI JELLEMZÉSÉNEK NÉHÁNY KÉRDÉSE pp. 1-5.
- B64 **Vizvári Z, Gyórfi N, Klincsik M, Sári Z, Odry P:** ÚJ MEGKÖZELÍTÉSŰ ELEKTROMOS IMPEDANCIA TOMOGRÁFIÁS REKONSTRUKCIÓS ALGORITMUS VALIDÁLÁSA ELLENÁLLÁS HÁLÓZATON pp. 1-10.
- B65 **Vizvári Z, Gyórfi N, Klincsik M, Sári Z, Odry P:** ÚJ MEGKÖZELÍTÉSŰ ELEKTROMOS IMPEDANCIA TOMOGRÁFIÁS REKONSTRUKCIÓS ALGORITMUS VALIDÁLÁSA IMPEDANCIA HÁLÓZATON pp. 1-11.



Session 7

- A71 **Novotni A:** THE ROLE OF THE RESEARCH OF WASTE AND BY-PRODUCTS OF WOOD INDUSTRY IN H2020 PROJECTS pp. 1-12.
- A72 **Gyórfi A, Jakab A R, Leitold Cs, Kiss T:** THE OBSERVATION OF PICKINGS IN A MANUAL SORTING PLANT OF SELECTIVELY COLLECTED MIXED PACKAGING WASTE FROM HOUSEHOLDS pp. 1-8.
- A73 **Gyórfi A, Leitold Cs, Kiss T, Dolgosné Kovács A:** THE STUDY OF SIZE AND COMPOSITION IN SELECTIVELY COLLECTED MIXED PACKAGING WASTE FROM HOUSEHOLDS pp. 1-9.
- A74 **Tahir C, Aktaş N:** SIMULATION AND OPTIMIZATION OF NATURAL GAS SWEETENING PLANT WITH HYSYS 8.0 pp. 1-9.
- A75 **Adamik P, Pásztor Z:** MEASUREMENT OF HEAT LOSS IN WOOD STEAMING KILN AND POSSIBILITY TO RECYCLING pp. 1-5.

Session 8

- B81 **Bokányi L, Hornyák G, Nagy S, Mádainé Üveges V:** LI-ION AKKUMULÁTOR BIOSZOLUBILIZÁLÁSÁNAK VIZSGÁLATA A FERROOXIDANS ÉS A FERRIDURANS BAKTÉRIUMMAL pp. 1-7.
- B83 **Varga B, Fodor K:** ECONOMIC STRENGTH – CRITICAL RAW MATERIAL STOCK pp. 1-9.
- B84 **Orosz D, Péter Zs:** EXAMINATION OF THE EXPECTED MARKET PRICE OF LITHIUM-BASED BATTERIES CURRENTLY OR IN THE FUTURE ON THE MARKET - MAIN TRENDS pp. 1-8.
- B85 **Yanar N:** LIMITATIONS IN PLASTIC RECYCLING, A REVIEW pp. 1-6.

Session 9

- A91 **Somfai D, Czakó-Vér K, Suhajda E, Dolgosné Kovács A, Dittrich E:** EXPERIMENTS OF ANAEROB CO-FERMENTATION OF THE BIODEGRADABLE FRACTION OF THE MUNICIPAL SOLID WASTES (BIFMSW) AND SEWAGE SLUDGE(S) pp. 1-5.
- A92 **Somfai D, Kósa D, Bicsák L, Suhajda E, Czakó-Vér K, Dolgosné Kovács A, Dittrich E:** MONITORING OF THE BIOLOGICAL ACTIVITY OF A BIOGAS PLANT WITH ENZYME ACTIVITY MEASUREMENTS pp. 1-8.
- A93 **Kalcsú Z, Pásztor Z:** THE CIRCULAR ECONOMY AND RECYCLING OF SECONDARY RAW MATERIALS pp. 1-5.
- A94 **Börcsök Z, Pásztor Z:** THE ROLE OF LIGNIN PLASTICIZATION IN SOME WOODWORKING PROCESSES pp. 1-11.
- A95 **Suhajda E, Somfai D, Czakó-Vér K, Dolgosné Kovács A, Dittrich E:** CO-FERMENTATIONAL AND QUALITY ASSURANCE ROLES OF SEWAGE SLUDGE IN BIOGAS PLANTS pp. 1-5.



Session 10

- B101 **Kornfeld Zs:** AZ ÖKOMARKETING LEHETŐSÉGEI, KÖRNYEZETVÉDELMI ELVÁRÁSAI ÉS AKADÁLYAI, AZAZ A FELMERÜLŐ KONTRA PROBLÉMÁK pp. 1-8.
- B102 **Szakálosné Mátyás K, Kovács K, Vityi A, Horváth A L:** LOGISZTIKA AZ AGROERDÉSZETBEN pp. 1-7.
- B103 **Kornfeld Zs:** A BESZERZÉS ÉRTELMEZÉSE A FAIPARI VÁLLALATOK KÖRÉBEN pp. 1-12.
- B104 **Kozák G, Major T:** ORSZÁGOS FELMÉRÉS A MOTORFŰRÉSZ HASZNÁLÓK KÖRÉBEN pp. 1-6.
- B105 **Szakálosné M K, Dudás T, Horváth A L:** MAGASAN GÉPESÍTETT EGÉSZSÉGÜGYI FAKITERMELESEK ELEMZÉSE pp. 1-9.

Session 11

- A111 **Vér Cs, Dolgosné Kovács A:** CHANGES IN THE LEGAL FRAMEWORK OF THE HUNGARIAN WASTE MANAGEMENT PUBLIC SERVICE SYSTEM AND THEIR ORGANIZATIONAL CONSEQUENCES AFTER 2015 pp. 1-9.
- A112 **Vér Cs, Dolgosné Kovács A:** FINANCIAL IMPACTS OF THE CENTRALIZATION OF THE HUNGARIAN WASTE MANAGEMENT PUBLIC SERVICE BETWEEN 2016 AND 2020 pp. 1-9.
- A113 **Hosakun W, Horváth D, Börcsök Z, Pásztory Z:** INSULATION BOARD MADE OF SAW DUST pp. 1-9.
- A114 **Kovács K, Czupy I, Hemida M, Vityi A:** POTENTIAL CONTRIBUTION OF AGROFORESTRY PRACTICES USED IN AGRICULTURAL AREAS pp. 1-7.
- A115 **Kornfeld Zs:** ECO-TENDENCIES REGARDING PELLETS pp. 1-10.

Session 12

- B121 **Porcsin A, Szakálosné M K:** A HAZAI FEHÉR AKÁC ERDŐTERÜLETEINEK, AZ AKÁCMÉZ MENNYISÉGÉNEK, ILLETVE A MÉHCSALÁDSZÁMOK VÁLTOZÁSÁNAK VIZSGÁLATA 2000-TŐL NAPJAINKIG pp. 1-7.
- B122 **Szunyog I, Szombati-Galyas A B:** A BIOMETÁN ÉS A HIDROGÉN HATÁSA A FÖLDGÁZRA BESZABÁLYOZOTT GÁZKÉSZÜLÉKEKBEN pp. 1-10.
- B125 **Kóczán Zs:** APPLICABILITY OF AFM IN PAPER RESEARCH pp. 1-8.

Agarwal Charu*, Pásztor Zoltán

Innovation Center, University of Sopron, Sopron 9400, Hungary

**Corresponding author email: charu.agarwal3@gmail.com*

TIP-ENHANCED RAMAN SPECTROSCOPY FOR NANOSCALE CHARACTERIZATION OF MATERIALS

ABSTRACT

Tip Enhanced Raman Spectroscopy (TERS) is a super-resolution analytical imaging technique that combines Raman spectroscopy and scanning probe microscopy. TERS has been used as a chemical characterization tool in a wide range of applications including materials science, chemical engineering and biology. This review explains TERS, while focusing on its various applications.

1. INTRODUCTION- CONCEPT AND PRINCIPLES



Tip Enhanced Raman Spectroscopy (TERS) has been a powerful microscopy technique for nanoscale characterization with growing applications ever since its inception in 2000 (1). The single nanoparticle at the probe or the tip generates a highly intense, evanescent field at the apex that interacts with the sample, as shown in Figure 1. The conventional Raman spectroscopy faces two major obstacles- low sensitivity and limited spatial resolution. The low sensitivity can be overcome by using surface-enhanced Raman scattering (SERS), where a strong electromagnetic field is generated on irradiating noble metal nanoparticles with a wavelength of light matching the plasmon resonance of the TERS tip. The limited resolution can be overcome by TERS that integrates the specificity of Raman spectroscopy with the nanoscale resolution of an atomic force microscope (AFM) by increasing the incident electromagnetic field by several orders of magnitude using the plasmonic nanostructures. A single plasmonic probe tip serves as both a Raman signal enhancing unit and a topography scanner (2).

TERS gives detailed information on the chemical composition including the molecular structure or conformation, defects, purity, etc. in a sample. A TERS system uses a metallic tip (gold or silver) that greatly enhances the Raman sensitivity (by a factor of 10^3 - 10^7) and reduces the probed volume of the test specimen to the nanoregion right below the tip (3).

2. INSTRUMENTATION

The AFM/Raman platform combines AFM with a confocal Raman spectrometer through an opto-mechanical coupling, which brings the excitation laser to the tip, while the spectrometer analyzes the Raman signal, thus producing an image with nanometer scale chemical contrast. There are two different configurations for this coupling- in transmission and reflection modes, with their own advantages and drawbacks. The configurations mainly differ by the irradiation patterns of the TERS tip (4,5). In bottom-illumination configuration, the laser beam is focused from the bottom through a transparent substrate (glass or mica) with a high numerical aperture (NA) objective ($NA \geq 1.4$), giving a high signal-to-noise ratio. In side illumination, the laser is incident on the sample at an angle of 45 – 70° , from the TERS tip. Top illumination enables asymmetric focusing that is tighter than that of side illumination with the help of a microscope objective ($NA=0.7$) or a parabolic mirror ($NA=1$).

The integrated platform can provide physical sample information at the nanometer scale, including topography, hardness, adhesion, friction, surface potential, electrical and thermal conductivity, temperature and piezo response, electrochemistry, along with the chemical information obtained from Raman spectroscopy and photoluminescence (6).



3. APPLICATIONS

TERS has been explored for a plethora of diverse applications ranging from material science to complex molecular biology (7,8). The following are some of the most interesting and recent applications of TERS (7,9,10):

a. Microbes: The structural composition of disease causing pathogens such as bacteria and viruses can be probed with TERS, which can facilitate the investigation of host-pathogen interactions, formation of biofilms and bacterial pathogenesis.

b. Biomolecules: Complex biological systems such as those with lipid membranes can be analyzed with TERS to provide a label-free measurement of molecular distribution on the cell membrane at the nanoscale and to gain insights into the molecular dynamics. Similarly, nucleic acids can be tested to identify or confirm their structure.


c. Proteins: The high sensitivity and spatial resolution of TERS can be used to investigate protein structures. It can assign marker bands for proteins and track their distribution in complex biological specimens.

d. Catalysis: TERS can be used for monitoring chemical reactions as well as molecular dynamics occurring at catalytic sites with nanoscale resolution. Recent studies have paved the way for the use of TERS for investigating heterogeneous catalytic reactions on solid-liquid and solid-gas interfaces.

e. Polymer blends: The surface of the polymer blends can be studied using TERS to reveal sub-surface information and information on the interfaces between the polymer blend components with a nanoscale resolution.

f. Semiconductors: TERS can play a crucial role in the chemical characterization of semiconductors such as silicon. The TERS tip induces a depolarization in the near-field, thus allowing separation of the distant-field signal contribution (polarized) from the near-field signal (depolarized).

g. Other materials: One-dimensional materials such as carbon nanotubes have been extensively investigated using TERS mapping to study the structural details including the fraction of crystalline and amorphous regions. TERS has also been employed to study other 1-D materials like CdSe and GaN nanowires. Similarly, 2-D materials have also been tested using TERS, a prominent example among them being graphene. The presence of defects, edges, and contaminated areas within graphene can be identified with sub-diffraction-limited resolution of TERS, which otherwise cannot be resolved using confocal Raman spectroscopy.



SUMMARY

In the past two decades, TERS has emerged as an effective label-free nondestructive tool for nanoscale chemical and structural characterization of material surfaces. It brings together the conventional Raman spectrometer with a scanning probe microscope, such as AFM on a single platform. TERS is an ambient technique and does not require high vacuum or cryogenic conditions for its operation and can be applied in air and liquid environments. The high sensitivity and nanoscale spatial resolution have made TERS an immensely sought-after technique for a myriad of applications. TERS has been extensively employed for the investigation of carbon nanotubes, graphene, semiconductors as well as various biological species such as proteins, lipids, nucleic acids, etc. Recent developments focus on the in situ use of TERS to monitor the chemical reactions, and derive information on the mechanisms and dynamics of the reactions.

ACKNOWLEDGEMENT

The work was carried out as part of the “Sustainable Raw Material Management Thematic Network – RING 2017”, EFOP-3.6.2-16-2017-00010 project in the framework of the Széchenyi 2020 Program. The realization of this project is supported by the European Union, co-financed by the European Social Fund.

REFERENCES

1. Zhang Z, Sheng S, Wang R, Sun M. Tip-enhanced Raman spectroscopy. *Anal Chem.* 2016;88(19):9328–46. Available from: <http://dx.doi.org/10.1021/acs.analchem.6b02093>
2. Deckert-Gaudig T, Taguchi A, Kawata S, Deckert V. Tip-enhanced Raman spectroscopy—from early developments to recent advances. *Chem Soc Rev.* 2017;46(13):4077–110. Available from: <http://dx.doi.org/10.1039/C7CS00209B>
3. Richard-Lacroix M, Zhang Y, Dong Z, Deckert V. Mastering high resolution tip-enhanced Raman spectroscopy: towards a shift of perception. *Chem Soc Rev.* 2017;46(13):3922–44. Available from: <http://dx.doi.org/10.1039/c7cs00203c>

4. Bonhommeau S, Lecomte S. Tip-enhanced Raman spectroscopy: a tool for nanoscale chemical and structural characterization of biomolecules. *ChemPhysChem*. 2018;19(1):8–18. Available from: <http://dx.doi.org/10.1002/cphc.201701067>
5. Yeo BS, Stadler J, Schmid T, Zenobi R, Zhang W. Tip-enhanced Raman spectroscopy - its status, challenges and future directions. *Chem Phys Lett*. 2009;472(1–3):1–13. Available from: <http://dx.doi.org/10.1016/j.cplett.2009.02.023>
6. Wang X, Huang SC, Huang TX, Su HS, Zhong JH, Zeng ZC, et al. Tip-enhanced Raman spectroscopy for surfaces and interfaces. *Chem Soc Rev*. 2017;46(13):4020–41. Available from: <http://dx.doi.org/10.1039/C7CS00206H>
7. Kumar N, Mignuzzi S, Su W, Roy D. Tip-enhanced Raman spectroscopy: principles and applications. *EPJ Tech Instrum*. 2015;2(1). Available from: <http://dx.doi.org/10.1140/epjti/s40485-015-0019-5>
8. Shao F, Zenobi R. Tip-enhanced Raman spectroscopy: principles, practice, and applications to nanospectroscopic imaging of 2D materials. *Anal Bioanal Chem*. 2019;411(1):37–61. Available from: <http://dx.doi.org/10.1007/s00216-018-1392-0>
9. Verma P. Tip-enhanced Raman spectroscopy: technique and recent advances. *Chem Rev*. 2017;117(9):6447–66. Available from: <http://dx.doi.org/10.1021/acs.chemrev.6b00821>
10. Voylov DN, Bocharova V, Lavrik N V., Vlassiuk I, Polizos G, Volodin A, et al. Noncontact tip-enhanced Raman spectroscopy for nanomaterials and biomedical applications. *Nanoscale Adv*. 2019;1(9):3392–9. Available from: <http://dx.doi.org/10.1039/c9na00322c>